

Acoustic properties of Acoustic Addition

manufactured by:

Screen Solutions Ltd.
 Beaufort House
 Greenwich Way
 Peacehaven
 East Sussex
 BN10 8 JQ
 United Kingdom



Acoustic Addition is symetrically constructed with the following components

- Fabric 1mm
- E70FR foam 25mm
- MDF board 12mm
- E70FR foam 25mm
- Fabric 1mm

Absorption Coefficient	Frequency Hz
0.12	125
0.20	250
0.45	500
0.60	1000
0.70	2000
0.81	4000

BS3638 reverberation room method
 measurements based on 25mm E70FR Acoustic Foam on 12mm MDF board

